

**Material: Glass**

**Method No. : L01**

**Results:**

The calcium carbonate crystal on the corroded surface of a glass.



**Preparation Method:**

**Cutting:** Abrasive Cut-off machine with Metlab Abrasive Wheels

**Mounting:** Cold Mounting

**Mechanical Preparation:** Metpol-A

Steps	Surface	Abrasive	Lubricant	Force per Sample, (N)/(PSI)	Time min.	Disc Speed, rpm	Relative Rotation
1	PIANO	YELLOW	Water	25/5	1	250	Contra
2	PIANO	BLUE	Water	25/5	1	300	Contra
3	Dac Cloth	3 $\mu$ Diamond Suspension	Blue Lube	15/3	4	150	Contra
4	Vellap Cloth	.25 $\mu$ Diamond Suspension	Blue Lube	15/3	4	150	Contra

**FOR MORE DETAILED INFORMATION PLEASE REFER TO METLAB PRICE LIST**